

Armamid PA6 GF 15-1T

A 15% glass fiber, elasticized polyamide 6. This material displays high mechanical and electrical properties; self-attenuates after the ignition source is exterminated; is resilient to nonpolar solvents, hydrocarbons (kerosene, gasoline, benzene etc.), mineral oils, strong and weak alkali, weak acids.

Designed for injection moulding of items and parts for a wide solutions range: construction, electronics, auto industry, machine engineering, aviation, household, transportation etc.

Available in grey, blue and black colors.

Properties	Test method	Unit	Typical value
MISCELLANEOUS			
Density	ISO 1183	kg/m ³	1220
Tensile Strength	ISO 527-1	MPa	120
Strain at Break	ISO 527-1	%	4
Flexural Stress at maximum load	ISO 178	MPa	170
Tensile Modulus	ISO 178	MPa	4900
Charpy Impact Strength at +23°C (un-notched)	ISO 179-1	kJ/m ²	40
Charpy Impact Strength at -40°C (un-notched)	ISO 179-1	kJ/m ²	30
Charpy Impact Strength at +23°C (notched)	ISO 179-1	kJ/m ²	6
THERMAL			
Melting Point	ISO 3146	°C	218
Deflection Temperature at 0.45 MPa load	ISO 75	°C	205
Deflection Temperature at 1.8 MPa load	ISO 75	°C	180
Coefficient of linear thermal expansion	ISO 11359-2	(10 ⁻⁶) ^K -1	30
Water absorption (23 °C, 24 h)	ISO 62	%	1.45
PROCESSING			
Melt Flow Rate (250 °C; 2,16 kg)	ISO 1133	g/10 min	12-20
Melt Temperature		°C	260
Mold Temperature		°C	80
Moulding Shrinkage, parallel	ISO 294-4	%	0.4-0.5
Moulding Shrinkage, normal	ISO 294-4	%	0.6-0.8
ELECTROPHYSICAL			
Electrical strength	IEC 60243	kV/mm	25
Specific volume resistivity	IEC 60093	Ω·m	1.00+E13
FLAMMABILITY			
Temperature resistance, hot wire ignition	IEC 60695-2-10	°C	650

Comment:

All processing parameters as well as information on shrinkage specimen should be requested from the manufacturer.

If stored in a dry warehouse – dehydration not required

Date of issue 10.04.2017

The information in this technical description is for reference purposes only. It can be considered as the basis for determining whether material is acceptable for specific applications. Because it is not possible to anticipate all applications of materials and operating conditions, POLYPLASTIC makes no warranty and assumes no liability for the use of the information specified in the catalog. This information may be changed without notice.