

Armamid PA6 GF 60-1

A 60% glass fibre polyamide 6. This material displays high mechanical and electrical properties; resilient to hydrocarbons (kerosene, gasoline, benzene etc.), mineral and synthetic oils, strong and weak alkali, weak acids.

Designed for injection moulding of items and parts for a wide solutions range: construction, electronics, auto industry, machine engineering, aviation, household, transportation etc.

Available in natural color.

Properties	Test method	Unit	Typical value
MISCELLANEOUS			
Density	ISO 1183	kg/m ³	1690
Tensile Strength	ISO 527-1/2	MPa	230
Flexural Stress at maximum load	ISO 178	MPa	350
Tensile Modulus	ISO 527-1/2	MPa	17500
Flexural Modulus	ISO 178	MPa	16500
Charpy Impact Strength at +23°C (un-notched)	ISO 179-1EU	kJ/m ²	90
Charpy Impact Strength at -40°C (un-notched)	ISO 179-1 EU	kJ/m ²	90
THERMAL			
Melting Point	ISO 3146	°C	220
Deflection Temperature at 1.8 MPa load	ISO 75	°C	220
PROCESSING			
Melt Temperature		°C	260
Mold Temperature		°C	80
Moulding Shrinkage, parallel	ISO 294-4	%	0.2-0.3
Moulding Shrinkage, normal	ISO 294-4	%	0.5-0.7
ELECTROPHYSICAL			
Electrical strength	IEC 60243	kV/mm	23
Specific volume resistivity	IEC 60093	Ω·m	1.00+E13
FLAMMABILITY			
Temperature resistance, hot wire ignition	IEC 60695-2-10	°C	650

Comment:

All processing parameters as well as information on shrinkage specimen should be requested from the manufacturer.

If stored in a dry warehouse – dehydration not required

Date of issue 28.08.2020

The information in this technical description is for reference purposes only. It can be considered as the basis for determining whether material is acceptable for specific applications. Because it is not possible to anticipate all applications of materials and operating conditions, POLYPLASTIC makes no warranty and assumes no liability for the use of the information specified in the catalog. This information may be changed without notice.